


BCB FLUTING



I

Typical characteristics

Property	Rif.	Units	Range						
Grammatura <i>Basis Weight</i>	ISO 536	g/m ²	+/-3%	90	100	105	110	120	
Umidità <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	
SCT, CD	ISO 9895	kN/m	-	1,15	1,25	1,28	1,3	1,45	
CMT 30, MD	ISO 7263	N	-	82	91	100	110	120	

Guaranteed Characteristics

Property	Rif.	Units							
SCT, CD	ISO 9895	kN/m	-	1,03	1,1	1,12	1,15	1,3	
CMT 30, MD	ISO 7263	N	-	75	82	90	95	105	

Intermill

CEPI code **61**

100 % RECYCLED

Applicazioni **carta da onda**

End uses *fluting for all types of application*

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : disponibile in versione FSC[®] o PEFC[™]

Certifications : available in FSC[®] or PEFC[™] version



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.