


BCB HP FROST



Typical characteristics

Property	Rif.	Units	Range										
Grammatura <i>Basis Weight</i>	ISO 536	g/m ²	+/-3%	115	120	130	135	140	150	160	170		
Umidità <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5		
SCT, CD	ISO 9895	kN/m	-	2,53	2,64	2,86	2,97	3,08	3,30	3,52	3,74		
CMT 30, MD	ISO 7263	N	-	253	264	286	297	308	330	352	374		
Cobb-60 max top	ISO 535	g/m ²		35 max	35 max	35 max	35 max	35 max	35 max	35 max	35 max		
Cobb-60 max bottom	ISO 535	g/m ²		35 max	35 max	35 max	35 max	35 max	35 max	35 max	35 max		

Guaranteed characteristics

Property	Rif.	Units	Range										
SCT, CD	ISO 9895	kN/m	-	2,30	2,40	2,60	2,70	2,80	3,00	3,18	3,38		
CMT 30, MD	ISO 7263	N	-	230	240	260	270	280	300	318	338		

Mill : Avezzano

CEPI code **45** 100 % RECYCLED

Applicazioni carta da onda per alte prestazioni e umido resistente
End uses High performance medium with high strength properties and moisture-resistant for fresh products packaging as fruits and vegetables (cool chain)

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : disponibile in versione FSC® o PEFC™
Certifications : available in FSC® or PEFC™ version



The mark of responsible forestry



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186
Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm
Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.