

BCB HS LINER



E

Typical characteristics

Property	Rif.	Units	Range												
Grammatura <i>Basis Weight</i>	ISO 536	g/m ²	+/-3%	100	110										
Umidità <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5										
SCT, CD	ISO 9895	kN/m	-	1,60	1,76										
Scoppio <i>Bursting Strenght</i>	ISO 2759	kPa	-	220	242										
Cobb 120" (top/back)	ISO 535	g/m ²	MAX	60	60										

Guaranteed characteristics

Property	Rif.	Units													
SCT, CD	ISO 9895	kN/m	-	1,45	1,59										
Scoppio <i>Bursting Strenght</i>	ISO 2759	kPa	-	200	220										

Intermill

CEPI code **32**

100 % RECYCLED

End uses *testliner with hard sizing top and back*

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : disponibile in versione FSC® o PEFC™
Certifications : available in FSC® or PEFC™ version



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.