


# BCB MEDIUM



I

## Typical characteristics

Property	Rif.	Units	Range											
Grammatura <i>Basis Weight</i>	ISO 536	g/m <sup>2</sup>	+/-3%	100	105	110	120	140						
Umidità <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5						
SCT, CD	ISO 9895	kN/m	-	1,29	1,35	1,42	1,55	1,91						
CMT 30, MD	ISO 7263	N	-	102	105	115	135	166						

## Guaranteed characteristics

Property	Rif.	Units	Range											
SCT, CD	ISO 9895	kN/m	-	1,12	1,22	1,28	1,40	1,68						
CMT 30, MD	ISO 7263	N	-	92	95	104	122	147						

## Mill : Intermill

CEPI code **43** 100 % RECYCLED

Applicazioni **carta da onda**  
End uses *fluting for all types of application*

*On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances*

Certificazioni : disponibile in versione FSC<sup>®</sup> o PEFC<sup>™</sup>  
Certifications : available in FSC<sup>®</sup> or PEFC<sup>™</sup> version



gen-21

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186  
Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm  
Sample analysis following the EN-ISO 187 norm conditions: 23 °C +/- 1°C, 50%+/-2% R.H.