

# BCB Medium HP/HP PLUS



## Typical characteristics

Property	Rif.	Units	Range										
Grammatura Basis Weight	ISO 536	g/m <sup>2</sup>	+/-3%	110	115	120	125	127	130	135	140		
Umidità Moisture Index	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5		
SCT, CD	ISO 9895	kN/m	-	2,26	2,36	2,46	2,56	2,60	2,67	2,77	2,87		
CMT 30, MD	ISO 7263	N	-	226	236	246	256	260	267	277	287		

## Guaranteed characteristics

Property	Rif.	Units	Range										
SCT, CD	ISO 9895	kN/m	-	2,05	2,14	2,23	2,32	2,35	2,42	2,51	2,60		
CMT 30, MD	ISO 7263	N	-	205	214	223	232	235	242	251	260		

## Mill : Avezzano

CEPI code **44**

100 % RECYCLED

Applicazioni **carta da onda per alte prestazioni**

End uses **High performance medium with high strength properties**

**On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances**

**Certificazioni : disponibile in versione FSC® o PEFC™**

**Certifications : available in FSC® or PEFC™ version**



The mark of responsible forestry



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.