

BCB Medium O-HP



Typical characteristics

Property	Rif.	Units	Range										
Grammatura <i>Basis Weight</i>	ISO 536	g/m ²	+/-3%	110	115	120	125	127	130	135	140		
Umidità <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5		
SCT, CD	ISO 9895	kN/m	-	2,42	2,53	2,64	2,75	2,79	2,86	2,97	3,08		
CMT 30, MD	ISO 7263	N	-	242	253	264	275	279	286	297	308		

Guaranteed characteristics

Property	Rif.	Units	Range										
SCT, CD	ISO 9895	kN/m	-	2,20	2,30	2,40	2,50	2,53	2,60	2,70	2,80		
CMT 30, MD	ISO 7263	N	-	220	230	240	250	253	260	270	280		

Mill : Avezzano

CEPI code **45**

100 % RECYCLED

Applicazioni **carta da onda per alte prestazioni**

End uses *High performance medium with high strength properties*

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : disponibile in versione FSC[®] o PEFC[™]

Certifications : available in FSC[®] or PEFC[™] version



The mark of responsible forestry



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.