

BCB Testliner 1



IE

Typical characteristics

Property	Rif.	Units	Range										
Grammatura <i>Basis Weight</i>	ISO 536	g/m ²	+/-3%	120	140	160	170						
Umidità <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5						
SCT, CD	ISO 9895	kN/m	-	2,40	2,80	3,20	3,40						
Scoppio <i>Bursting Strenght</i>	ISO 2759	kPa	-	370	432	450	524						
Cobb-60 max	ISO 535	g/m ²	-	30 max	30 max	30 max	30 max						

Guaranteed characteristics

Property	Rif.	Units											
SCT, CD	ISO 9895	kN/m	-	2,17	2,50	2,88	3,01						
Scoppio <i>Bursting Strenght</i>	ISO 2759	kPa	-	335	391	405	474						

Mill : Avezzano

CEPI code 10

100 % RECYCLED

Applicazioni carta collata per copertina avana

End uses testliner sized paper for cost effective general purpose packaging

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : disponibile in versione FSC[®] o PEFC[™]

Certifications : available in FSC[®] or PEFC[™] version



The mark of responsible forestry



Promoting Sustainable Forest Management
www.pefc.org

nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.