

# BCB Testliner 2



## Typical characteristics

Property	Rif.	Units	Range										
<b>Grammatura</b> <i>Basis Weight</i>	ISO 536	g/m <sup>2</sup>	+/-3%	110	115	120	130	140	160	170			
<b>Umidità</b> <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	7,5	7,5			
<b>SCT, CD</b>	ISO 9895	kN/m	-	1,85	2,10	2,20	2,40	2,60	3,00	3,10			
<b>Scoppio</b> <i>Bursting Strenght</i>	ISO 2759	kPa	-	297	310	324	351	378	432	455			
<b>Cobb-60 max</b>	ISO 535	g/m <sup>2</sup>	-	35 max	35 max	35 max	35 max	35 max	35 max	35 max			

## Guaranteed characteristics

Property	Rif.	Units											
<b>SCT, CD</b>	ISO 9895	kN/m	-	1,70	1,90	2,00	2,20	2,40	2,70	2,80			
<b>Scoppio</b> <i>Bursting Strenght</i>	ISO 2759	kPa	-	268	280	293	317	342	390	411			

## Mill : Avezzano

**CEPI code** 20 100 % RECYCLED

**Applicazioni** carta collata per copertina avana  
**End uses** testliner sized paper for cost effective general purpose packaging

*On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances*

**Certificazioni** : disponibile in versione FSC® o PEFC™

*Certifications* : available in FSC® or PEFC™ version



The mark of responsible forestry



Promoting Sustainable Forest Management  
 www.pefc.org

nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

*Campioni prelevati secondo la Norma EN-ISO 186*

*Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.*

*Sample collection following the EN-ISO 186 norm*

*Sample analysis following the EN-ISO 187 norm conditions:*

23 °C +/- 1°C, 50%+/-2% R.H.