

BCB Testliner 3



IE

Typical characteristics

Property	Rif.	Units	Range																
Grammatura Basis Weight	ISO 536	g/m ²	+/-3%	80	85	90	100	105	110	120	125	130	135	140	150	160	190		
Umidità Moisture Index	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5		
SCT, CD	ISO 9895	kN/m	-	1,28	1,36	1,44	1,60	1,68	1,76	1,92	2,00	2,15	2,23	2,31	2,48	2,64	3,00		
Scoppio Bursting Strenght	ISO 2759	kPa	-	182	194	205	220	231	242	264	275	286	297	308	330	352	415		
Cobb-60 max	ISO 535	g/m ²	-	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max		

Guaranteed characteristics

Property	Rif.	Units																	
SCT, CD	ISO 9895	kN/m	-	1,15	1,22	1,30	1,45	1,52	1,59	1,74	1,81	1,95	2,02	2,09	2,24	2,39	2,70		
Scoppio Bursting Strenght	ISO 2759	kPa	-	164	174	185	200	210	220	238	248	258	268	278	298	318	374		

Intermill

CEPI code **30**

100 % RECYCLED

Applicazioni **carta collata per copertina avana**

End uses **testliner sized paper for cost effective general purpose packaging**

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : disponibile in versione FSC® o PEFC™

Certifications : available in FSC® or PEFC™ version



Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1 °C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1 °C, 50%+/-2% R.H.