

# BCB Testliner 3



IE

## Typical characteristics

Property	Rif.	Units	Range																
<b>Grammatura</b> <i>Basis Weight</i>	ISO 536	g/m <sup>2</sup>	+/-3%	80	85	90	100	105	110	120	125	130	135	140	150	160			
<b>Umidità</b> <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5			
<b>SCT, CD</b>	ISO 9895	kN/m	-	1,28	1,36	1,44	1,60	1,68	1,76	1,92	2,00	2,15	2,23	2,31	2,48	2,64			
<b>Scoppio</b> <i>Bursting Strenght</i>	ISO 2759	kPa	-	182	194	205	220	231	242	264	275	286	297	308	330	352			
<b>Cobb-60 max</b>	ISO 535	g/m <sup>2</sup>	-	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max			

## Guaranteed characteristics

Property	Rif.	Units																	
<b>SCT, CD</b>	ISO 9895	kN/m	-	1,15	1,22	1,30	1,45	1,52	1,59	1,74	1,81	1,95	2,02	2,09	2,24	2,39			
<b>Scoppio</b> <i>Bursting Strenght</i>	ISO 2759	kPa	-	164	174	185	200	210	220	238	248	258	268	278	298	318			

## Intermill

CEPI code **30**

**100 % RECYCLED**

**Applicazioni** carta collata per copertina avana  
**End uses** testliner sized paper for cost effective general purpose packaging

*On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances*

**Certificazioni** : disponibile in versione FSC® o PEFC™  
*Certifications* : available in FSC® or PEFC™ version



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

*Campioni prelevati secondo la Norma EN-ISO 186*  
*Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.*

*Sample collection following the EN-ISO 186 norm*  
*Sample analysis following the EN-ISO 187 norm conditions: 23 °C +/- 1°C, 50%+/-2% R.H.*