

# BCB Testliner 4

IE

## Typical characteristics

Property	Rif.	Units	Range														
Grammatura Basis Weight	ISO 536	g/m <sup>2</sup>	+/-3%	100	105	110	112	115	130	135	160	170					
Umidità Moisture Index	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5					
SCT, CD	ISO 9895	kN/m	-	1,30	1,37	1,43	1,46	1,5	1,69	1,76	2,08	2,21					
Scoppio Bursting Strenght	ISO 2759	kPa	-	170	178	187	190	195	221	229	256	272					

## Guaranteed characteristics

Property	Rif.	Units															
SCT, CD	ISO 9895	kN/m	-	1,18	1,24	1,29	1,32	1,36	1,53	1,59	1,88	2,00					
Scoppio Bursting Strenght	ISO 2759	kPa	-	153	161	169	171	176	200	207	231	246					

## Intermill

CEPI code **38**

100 % RECYCLED

Applicazioni **carta per copertina avana**

End uses **testliner paper for cost effective general purpose packaging**

*On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances*

Certificazioni : disponibile in versione FSC<sup>®</sup> o PEFC<sup>™</sup>

Certifications : available in FSC<sup>®</sup> or PEFC<sup>™</sup> version



Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.

nov-20