

BCB WELLENSTOFF



IE

Typical characteristics

Property	Rif.	Units	Range																
Grammatura Basis Weight	ISO 536	g/m ²	+/-3%	70	75	80	85	90	100	105	110	115	120	125	127	130	135		
Umidità Moisture Index	ISO 287	%	+/-1%	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5		
SCT, CD	ISO 9895	kN/m	-	1,07	1,15	1,44	1,53	1,62	1,80	1,89	2,00	2,07	2,16	2,25	2,29	2,34	2,43		
CMT 30, MD	ISO 7263	N	-	60	70	112	120	145	160	168	176	184	192	200	203	208	216		

Guaranteed characteristics

Property	Rif.	Units																	
SCT, CD	ISO 9895	kN/m	-	0,97	1,04	1,30	1,38	1,46	1,62	1,71	1,81	1,87	1,95	2,04	2,07	2,11	2,20		
CMT 30, MD	ISO 7263	N	-	54	63	101	111	130	144	152	159	166	173	181	183	188	195		

Intermill

CEPI code **41** **100 % RECYCLED**

Applicazioni **carta da onda**
End uses *fluting for all types of application*

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : **disponibile in versione FSC® o PEFC™**
Certifications : *available in FSC® or PEFC™ version*



Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.

nov-20