


# BCB DUAL



## Typical characteristics

| Property       | Rif.     | Units            | Range |      |     |  |  |  |  |  |  |  |  |  |  |
|----------------|----------|------------------|-------|------|-----|--|--|--|--|--|--|--|--|--|--|
| Basis Weight   | ISO 536  | g/m <sup>2</sup> | +/-3% | 85   | 120 |  |  |  |  |  |  |  |  |  |  |
| Moisture Index | ISO 287  | %                | +/-1% | 7,5  | 7,5 |  |  |  |  |  |  |  |  |  |  |
| SCT, CD        | ISO 9895 | kN/m             | -     | 1,50 | 2,2 |  |  |  |  |  |  |  |  |  |  |
| CMT 30, MD     | ISO 7263 | N                | -     | 115  | 195 |  |  |  |  |  |  |  |  |  |  |
| Burst strength | ISO 2759 | kPa              | -     | 200  | 280 |  |  |  |  |  |  |  |  |  |  |
| Cobb-60 max    | ISO 535  | g/m <sup>2</sup> | -     | 35   | 35  |  |  |  |  |  |  |  |  |  |  |

## Guaranteed characteristics

| Property       | Rif.     | Units |   |      |      |  |  |  |  |  |  |  |  |  |  |
|----------------|----------|-------|---|------|------|--|--|--|--|--|--|--|--|--|--|
| SCT, CD        | ISO 9895 | kN/m  | - | 1,40 | 2,00 |  |  |  |  |  |  |  |  |  |  |
| CMT 30, MD     | ISO 7263 | N     | - | 105  | 170  |  |  |  |  |  |  |  |  |  |  |
| Burst strength | ISO 2759 | kPa   | - | 170  | 240  |  |  |  |  |  |  |  |  |  |  |

## Mill : Verzuolo

CEPI code **52** **100 % RECYCLED**

End uses **high performance double purpose sized paper**

*On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances*

Certifications : available in FSC® or PEFC™ version



The mark of responsible forestry



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions: 23 °C +/- 1°C, 50%+/-2% R.H.