


BCB MEDIUM TOP HC



Typical characteristics

Property	Rif.	Units	Range											
Grammatura <i>Basis Weight</i>	ISO 536	g/m ²	+/-3%	115	135									
Umidità <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5									
SCT, CD	ISO 9895	kN/m	+/-6%	2,36	2,77									
CMT 30, MD	ISO 7263	N	+/-6%	236	277									
RCT MD	ISO 12192	kN/m	+/-6%	1,8	2,0									

Mill : Avezzano

CEPI code 61 100 % RECYCLED

Applicazioni carta da onda per honeycomb
End uses fluting for honeycomb

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : disponibile in versione FSC® o PEFC™
Certifications : available in FSC® or PEFC™ version



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186
Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm
Sample analysis following the EN-ISO 187 norm conditions: 23 °C +/- 1°C, 50%+/-2% R.H.