

# BCB TESTLINER HC



I

## Typical characteristics

Property	Rif.	Units	Range										
<b>Grammatura</b> <i>Basis Weight</i>	ISO 536	g/m <sup>2</sup>	+/-3%	110	130	170							
<b>Umidità</b> <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5	7,5							
<b>SCT, CD</b>	ISO 9895	kN/m	+/-6%	1,76	2,15	2,72							
<b>Scoppio</b> <i>Bursting Strenght</i>	ISO 2759	kPa	+/-6%	242	286	374							
<b>Cobb-60 max top</b>	ISO 535	g/m <sup>2</sup>		37 max	37 max	37 max							
<b>Cobb-60 max bottom</b>	ISO 535	g/m <sup>2</sup>		55 max	55 max	55 max							
<b>RCT MD</b>	ISO 12192	kN/m	+/-6%	1,6	1,8	2,0							

## Mill : Avezzano

**CEPI code** 50

100 % RECYCLED

**Applicazioni** carta per copertina avana per honeycomb

*End uses* testliner paper for honeycomb

*On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances*

**Certificazioni : disponibile in versione FSC® o PEFC™**

*Certifications : available in FSC® or PEFC™ version*



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

*Campioni prelevati secondo la Norma EN-ISO 186*

*Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.*

*Sample collection following the EN-ISO 186 norm*

*Sample analysis following the EN-ISO 187 norm conditions:*

*23 °C +/- 1°C, 50%+/-2% R.H.*