

BCB TESTLINER UP HC



I

Typical characteristics

Property	Rif.	Units	Range										
Grammatura <i>Basis Weight</i>	ISO 536	g/m ²	+/-3%	130	170								
Umidità <i>Moisture Index</i>	ISO 287	%	+/-1%	7,5	7,5								
SCT, CD	ISO 9895	kN/m	+/-6%	2,40	3,10								
Scoppio <i>Bursting Strenght</i>	ISO 2759	kPa	+/-6%	351	455								
Cobb-60 max top	ISO 535	g/m ²		37 max	37 max								
Cobb-60 max bottom	ISO 535	g/m ²		55 max	55 max								
RCT MD	ISO 12192	kN/m	+/-6%	2,0	2,1								

Mill : Avezzano

CEPI code 50

100 % RECYCLED

Applicazioni carta per copertina avana per honeycomb

End uses testliner paper for honeycomb

On demand available grammages out of TDS, with agreement on minimum lot, production optimization and tolerances

Certificazioni : disponibile in versione FSC[®] o PEFC[™]

Certifications : available in FSC[®] or PEFC[™] version



nov-20

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Campioni prelevati secondo la Norma EN-ISO 186

Analisi eseguite secondo le condizioni della Norma EN-ISO 187: 23 °C +/- 1°C, 50%+/-2% R.H.

Sample collection following the EN-ISO 186 norm

Sample analysis following the EN-ISO 187 norm conditions:

23 °C +/- 1°C, 50%+/-2% R.H.